

CLAIMS

1. A process for producing a synthetic resin film,
comprising:

5 (A) a step of casting and applying a composition
containing a polymer and an organic solvent onto a support
to form a gel film;

(B) a step of stripping the gel film and heating the
gel film with both ends being fixed; and

10 (C) a step of heating the film with both ends being
released after step (B), wherein the thickness b of the film
produced in step (B) and the thickness c of the film
produced in step (C) satisfy the relationship $b > c$.

15 2. The process for producing the synthetic resin film
according to Claim 1, wherein heating in step (C) is
performed under a tension of 0.10 to 1.50 kg/mm² in the
machine direction (MD) of the film.

20 3. The process for producing the synthetic resin film
according to Claim 1 or 2, wherein heating in step (B) is
performed at a maximum atmospheric temperature of 450°C or
lower.

25 4. The process for producing the synthetic resin film

according to any one of Claims 1 to 3, wherein heating in step (B) is performed by treatment with hot air.

5. The process for producing the synthetic resin film according to any one of Claims 1 to 3, wherein heating in step (B) is performed by treatment with radiant heat rays.

6. The process for producing the synthetic resin film according to any one of Claims 1 to 3, wherein heating in step (B) is performed by a combination of hot air treatment and radiant heat rays treatment.

7. The process for producing the synthetic resin film according to any one of Claims 1 to 6, wherein heating in step (C) is performed at an atmospheric temperature of 430°C or higher.

8. The process for producing the synthetic resin film according to any one of Claims 1 to 7, wherein heating in step (C) is performed by treatment with hot air.

9. The process for producing the synthetic resin film according to any one of Claims 1 to 7, wherein heating in step (C) is performed by treatment with radiant heat rays.

10. The process for producing the synthetic resin film according to any one of Claims 1 to 7, wherein heating in step (C) is performed by a combination of hot air treatment and radiant heat rays treatment.

5

11. The process for producing the synthetic resin film according to any one of Claims 1 to 7, wherein heating in step (C) is performed by simultaneous treatment with hot air and radiant heat rays.

10

12. The process for producing the synthetic resin film according to any one of Claims 1 to 11, wherein the synthetic resin film comprises a polyimide.

15

13. A process for producing a synthetic resin film, comprising:

(A) a step of casting and applying a composition containing a polymer and an organic solvent onto a support to form a gel film;

20

(B) a step of stripping the gel film and heating the gel film with both ends being fixed; and

(C) a step of heating the film with both ends being released after step (B), wherein the heating temperature in step (B) is higher than that in step (C).

25

14. The process for producing the synthetic resin film according to Claim 13, wherein heating in step (B) is performed at a maximum atmospheric temperature of 450°C or lower.

5

15. The process for producing the synthetic resin film according to Claim 13 or 14, wherein heating in step (C) is performed at an atmospheric temperature of 430°C or higher.

10 16. The process for producing the synthetic resin film according to any one of Claims 13 to 15, wherein the synthetic resin film comprises a polyimide.